

**Technical Data Sheet****Rubber Accelerator CBS (CZ)**

06/08/2016

CAS No.: 95-33-0

Chemical Name:

N-Cyclohexyl-2-benzothiazole sulfenamide
It is similar to Santocure CBS, Vulkacit CZ, Nocceler CZ, Delac S, Accicure HBS

Technical Specification:

Item	Technical Specifications
Appearance	Grayish-white, light yellow powder, granular
Melting point	°C min. 98.0
Heating Loss	% max. 0.30
Ash Content	% max. 0.30
Residues on 150µm sieve	% max. 0.05
Insoluble in methanol	% max. 0.50
Free amine	% max. 0.50
Purity	% min. 97.0

Properties:

Slightly odor and non-toxic.
Soluble in benzene, methylene chloride, carbon tetrachloride, ethyl acetate and acetone, slightly soluble in ethanol and gasoline, insoluble in water.

Application:

Accelerator CBS (CZ) is an accelerator with high activity and has greatly delayed action, high anti-scorching quality, processing safety, short cure time. Its activity can be reinforced by thiuram and dithiocarbamate type alkaline accelerators. Mainly used in manufacture of tires, rubber shoes, rubber tube and other rubber products.

Package:

In woven bag or kraft paper bag lined with PE film bag, net weight: 25Kg/bag.

Storage:

Stored at room temperature.

Precaution:

Please refer to the appropriate material safety data sheet (MSDS) prior to Using this product.
FOR INDUSTRIAL USE ONLY.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not Intended for design purposes.