

**Technical Data Sheet****Rubber Accelerator TBBS (NS)**

06/08/2016

CAS No.: 95-31-8

Chemical Name:N-Tertiarybutyl-2-benzothiazole sulfenamide
It is similar to Santocure TBBS, Vulkacit NZ, Delac NS, Accicure BSB**Technical Specification:**

Item	Technical Specifications
Appearance	White or light yellow powder, granular
Melting point °C min.	104.0
Heating Loss % max.	0.40
Ash Content % max.	0.30
Residues on 150µm sieve % max.	0.10
Insoluble in methanol % max	1.00
Free amine % max	0.50
Purity % min.	96.0

Properties:

Soluble in benzene, chloroform, carbon disulfide, acetone, methanol, ethanol, but hard in gasoline, insoluble in water, dilute acid and dilute alkali.

Application:

Accelerator TBBS (NS) is a vulcanization accelerator with delayed action, short cure time, has high anti-scorching quality, processing safety. Widely used in all sorts of rubber products and tires, especially the meridian tires. The product is an excellent delayed accelerator with more delayed action and great curing rate and other advantages.

Package:

In woven bag or kraft paper bag lined with PE film bag, net weight: 25Kg/bag.

Storage:

Stored at room temperature.

Precaution:

Please refer to the appropriate material safety data sheet (MSDS) prior to Using this product.

FOR INDUSTRIAL USE ONLY.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not Intended for design purposes.